

Tipologia Produttiva : **Monocottura da Rivestimento**
 Productive Typologies: **Single Fired Wall tiles**











Formati / Sizes : **20x20 (8"x8")**

Superficie: **Satinata**
 Finish: **Satin**

Bordi / Edges: **Naturale / Natural**



ISO 13006 UNI EN 14411 - APPENDICE L - BIII

CARATTERISTICHE TECNICHE	NORMA		THESI
 spessore thickness épaisseur Stärke	10545.2	± 10 %	9,5 mm
 lunghezza e larghezza length and width longueur et largeur Länge und Breite		± 0,3 %	± 0,3 %
 rettezza degli spigoli straightness of sides rectilignité des arêtes Kantengeradheit		± 0,3 %	± 0,3 %
 ortogonalità wedging orthogonalité Rechtwinkligkeit		± 0,3 %	± 0,3 %
 planarità flatness planéité Ebenflächigkeit		+0,8mm -0,2mm	+0,8mm -0,2mm
 assorbimento d'acqua water absorption absorption d'eau Wasseraufnahme	10545.3	valore medio > 10%	valore medio > 10%
 resistenza alla flessione bending strength résistance à la flexion Biegefestigkeit	10545.4	spessore ≥ 7,5mm - 15 N/mm ² minimo	15 N/mm²
sfuerzo di rottura (S) breaking strength (S) chargement de rupture (S) Bruchlast (S)		spessore ≥ 7,5mm - 600 N minimo	600 N
 resistenza al cavillo crazing resistance résistance au tressillage Harrißbeständigkeit	10545.11	richiesta required demandée Erforderlich	garantita guaranteed garantie Garantiert
 resistenza ai prodotti chimici di uso domestico e additivi per piscina resistance to household chemicals and swimming-pool additives résistance aux produits chimiques d'usage domestique et additifs pour piscine Beständigkeit gegen Haushaltschemikalien und Badewasserzusätze für Schwimmbäder	10545.13	GB minimo	GA
 resistenza alle macchie stain resistance résistance aux taches Fleckenfestigkeit		10545.14	Classe 3 minimo